



PROPERTIES:

Form	Grey free flow powder
Mixed Density	2.18 to 2.28 Kg/Lit.
Expansion	0.1 to 0.5% after 28 days.
Compressive Strength at 27 deg.C(approx.) after 3 days	300 Kg/Sq.Cm(min.)
after 28 days	500 Kg/Sq.Cm(min.)

SHELF LIFE:

Six Months from the date of manufacture. Material should be stored in a perfectly dry place.

PACKING:

50 kgs in Poly lined HDPE bags

HANDLING PRECAUTION:

Grout Ns 500 is non-toxic and ingestion is to be avoided. Any splashes to the skin must be washed with water. If contact with eyes occurs, wash well immediately with water and seek medical advice.

NOTE:

- Eastern Setcrete has a team of trained professionals to provide technical support to your problems in construction, particularly to recommend the correct product for a specific application. We can also send our authorized applicator to apply our products at your site.
- Contents of this data sheet are only indicative and not conclusive. All the results shown here are generated from our laboratory or from our own site experiences.
- The quality of all our products are maintained as per ISO:9001 recommendations and continuous research, but conditions prevailing at the point of application can vary its behavior.

Corporate Office:

P-89, C.I.T. Road, Kolkata - 700 010 Phone : 2353-9279 / 23632470.

Fax : 91-33-23733078 E-mail : setcrete@yahoo.com,

Website : www.setcrete.com

JAS-ANZ

