



Typical Performance of Set Rapid							
Curing Temp.	Dosage of Admixture Lit/ 100 kg.	Initial Set, hrs.	Final Set, hrs	Compressive strength 1 day	Compressive strength 3 days	Compressive strength 7 days	Compressive strength 28 days
5 C	Nil	14	19	1.5	5.5	17	32
10 C	2.5	12	17	3	10	20	36
20 C	Nil	4	6	2.5	8	20	35
	2.5	3	4.5	4.5	13	24	40
	Nil	3	4.5	6	17	27	43
	2.5	1.5	3.5	11	28	36	48

SHELF LIFE:

18 months from the date of manufacture. Material should be stored in a dry place.

PACKING:

25 kg, 120 kg, 250 kg in HDPE container.

HANDLING PRECAUTION:

Set Rapid is formulated from chemicals which create no health hazards and no fire.

NOTE:

- Eastern Setcrete has a team of trained professionals to provide technical support to your problems in construction, particularly to recommend the correct product for a specific application. We can also send our authorized applicator to apply our products at your site.
- Contents of this data sheet are only indicative and not conclusive. All the results shown here are generated from our laboratory or from our own site experiences.
- The quality of all our products are maintained as per ISO:9001 recommendations and continuous research, but conditions prevailing at the point of application can vary its behavior.

SETCRETE

Corporate Office:

P-89, C.I.T. Road, Kolkata - 700 010 Phone : 2353-9279 / 23632470.

Fax : 91-33-23733078 E-mail : setcrete@yahoo.com,

Website : www.setcrete.com

JAS-ANZ

